Turkish Online Journal of Qualitative Inquiry (TOJQI) Volume 12, Issue 7, July 2021: 5224- 5232

Research Article

Optimization of Hybrid CFRP Composites with AHP-Topsis Method in Mechanical charecteriztion

Ch. Siva RamaKrishna¹, Dr.N.Ramanaiah²

Abstract

The purpose of the present study is to investigate the direct relationship between mechanical properties such as tensile strength, tensile modulus, flexural strength, hardness, Impact strength and flexural modulus. The impact of graphite powder combined with epoxy LY556 and HY-951 hardeners, as well as the performance of hybrid composites, were determined. In the same way, CFRP and basalt composites with varying stacking sequences are investigated in the same way. Using AHP-TOPSIS, it was possible to optimise the mechanical characterization of a composite hybrid. The results of this study offer an analytical model for composite materials that may be used to categorise materials

Keywords: Hybrid composites, Hand-Lay Up, CFRP, Mechanical characterization, AHP-TOPSIS Method. Ranking.

1 Introduction

In the current research, the direct links between mechanical characteristics such as tensile strength, tensile module, flexural strength ,flexural module, Impact strength and hardness are investigated.Graphite powder strength coupled with epoxy hardener LY556 and HY-951 was measured as well as the performanc of hybrid composites. CFRPs and basalt composites are also studied in the same manner with different stacking sequences. The mechanical characterisation of a composite hybrid has been optimised using AHP-TOPSIS. The findings of this research provide a composite material analysis model which may be utilised for the categorisation of materials.

2. LITERATURE REVIEW

Hybrid composites combine the effect strength, tensile module, and compressive strength characteristics not obtainable from composite materials[1]. The constructions are very weight-resistant and have excellent plastic enhanced fibre corrosion (FRP). A numerical computation is carried out in Taylor and Nayfeh for simple composition layered, thick plates

¹Research Scholar, Department of Mechanical Engineering College of Engineering, Andhra University, Visakhapatnam

²Professor, Department of Mechanical Engineering, College of Engineering, Andhra University, Visakhapatnam

that support free vibration[2]. They examine the impact on vibration by change the inherent frequencies of microstructures and bonding agents[3-6].AHP-TOPSIS method was utilised by Mansor et al. to rank the composites hybrid natural fibre materials used for the car parking brake lifting component. The electronic copper cathode procurement has identified eight factors, i.e. quality, availability, origin, costs, transportation costs, delivery requirements, quality certifications and supplier dependability[7-11].The ranking analysis was conducted using the measured data to identify the most meaningful material for better performance.

3 Methodologies

The materials and techniques utilised in the production of studied composites are explained in this chapter. It shows mechanical characterisation in tensile, flexural, hardness and impact testing of hybrid composites. Experimental technique based on specimen 3.1 Mixed manufacturing: In order to produce fiber-enhanced epoxy composites CFRP and basaltic fibre composites were independently strengthened in epoxy resin.. Conventional hand lay-up processes have produced these composite panels. The specifics and identification of the prepared composites are provided in the manufacturing procedure Table 3.1.

Table 3.1 Detailed designation and composition of composites					
Composites	Composition				
CCCC	Epoxy (42%) + COCC (58%)				
BBBB	Epoxy (36%) +BBBB (64%)				
CBCB	Epoxy (39%) + CBCB (61%)				
BCCB	Epoxy (39%) + BCCB (61%)				
CBBC	Epoxy (39%) + CEBC (61%)				
CCCC + 1% graphite	Epoxy (41%) + COCC (58%) + Graphite (1%)				
BBBB + 1% graphite	Epoxy (35%) + BEBB (64%) + Graphite (1%)				
CBCB + 1% graphite	Epoxy (38%) + CBCB (61%) + Graphite (1%)				
BCCB + 1% graphite	Epoxy (38%) + BCCB (61%) + Graphite (1%)				
CBBC + 1% graphite	Epoxy (38%) + CEBC (61%) + Graphite (1%)				
CCCC + 2% graphite	Epoxy (40%) + CCCC (58%) + Graphite (2%)				
BBBB + 2% graphite	Epoxy (34%) + BEBB (64%) + Graphite (2%)				
CBCB + 2% graphite	Epoxy (37%) + CBCB (61%) + Graphite (2%)				
BCCB + 2% graphite	Epoxy (37%) + BCCB (61%) + Graphite (2%)				
CBBC + 2% graphite	Epoxy (37%) + CEBC (61%) + Graphite (2%)				
CCCC + 3% graphite	Epoxy (39%) + CCCC (58%) + Graphite (3%)				
BBBB + 3% graphite	Epoxy (33%) + BEBB (64%) + Graphite (3%)				
CBCB + 3% graphite	Epoxy (36%) + CBCB (61%) + Graphite (3%)				
BCCB + 3% graphite	Epoxy (36%) + BCCB (61%) + Graphite (3%)				
CBBC + 3% graphite	Epoxy (36%) + CEBC (61%) + Graphite (3%)				

The two-way composites CFRP and Basalt together with epoxy resin and hardener are independently produced by hand-laying in composites. A high quality surface initially applies to cover to the mould. When the gel coat is adequately dried, glass fibre reinforcement of the rolling stock is put manually on the mould.



For the ranking of materials, the following method, AHP-TOPSIS, is utilised. In designing any products or components, material selection plays a very significant role. AHP may be implemented in three easy steps: weight of the option scoring criterion vector matrix, and option ranking. The standard specimen with end-tabs are the most frequently utilised specimen geometries. The ASTM D 3039-76 standard test technique was utilised.the following steps are followed for AHP-TOPSIS method

Step 1:-For weighing purposes, a three-level hierarchical structure is constructed. At the first level, the objective of the research is to classify the composites for usage-proof applications. The study criteria are displayed at the second level. Tensile strength, tensile modulus, flexural strength and flexural modulus, impact strength and hardness. The third hierarchy includes the alternatives, i.e. a range of materials, which are classified as the best option.

Step 2:-In order to compute the weighing of various criteria, the AHP begins with the establishment of a pair-wise comparison matrix, A (m alternatively), where m is the number of alternative evaluations taken into account and n is the number of criteria. The significance of the i th criteria relative to the jth criterion is represented by each A _{ij} member of matrix A. If the ith criteria are greater than the jth criterion, then the ith criterion is less significant than the jth criterion, whereas a_i is less important than the jth criterion.

Intensity	Definition
1	Equal importance
3	Moderate importance
5	High importance
7	Very importance
9	Extreme importance
2 4 6 8	Intermediate values
Reciprocals	Reciprocal for comparison

$$A = \begin{bmatrix} 1 & a_{12} & a_{13} & \cdots & a_{1j} \\ a_{21} & 1 & a_{23} & \cdots & a_{2j} \\ a_{31} & a_{32} & \ddots & \cdots & a_{3j} \\ \vdots & \vdots & \vdots & \ddots & \vdots \\ a_{i1} & a_{i2} & a_{i3} & \cdots & a_{ij} \end{bmatrix}$$

If the significance of two criteria is the same, the entry is 1. The Aij and Aji entries meet the following limitations: $* aji = 1 Aij^*$

Step 4:-Each cell will use Xij = Cij / TOCIJ standardised

Phase 5:- Calculation is performed on the row value ri = alleviation Xij of the standardised matrix for pairs.

Step 6:-If you are using Wi = To dxij /n, whereby n is the number of criteria, you calculate the weight of the conditions.

Step 7:- Vi = Ai * Wi for i = 1, 2, 3, ..., n is used for the vector priorities

Step 8:- Calculates the μ i vector and determines the main own value of the whole value (by averaging the own vector values).

Step 9: - The Equation is used as the consistency index (CI).

Step 10:- Ratio of coherence (RC) is achieved through. The Random Incoherence Index (RI) is determined by n. RI values between 1-10 matching to n

n 1 2 3 4 5 6 7 8 0 10 0.58 0.9 RI 0.00 0.00 1.12 1.24 1.32 1.41 1.46 1.149

TOPSIS method is used for ranking purpose and the steps are mentioned below;

Step 1:- Determination of the decision matrix: The decision matrix, X, can be represented as follows

where A_i represent alternative maintenance i, i = 1,...,m and Bj denotes decision criteria j, j = 1,...,n of which alternatives are judged. x_{ij} represent jth criteria with respect to ith alternative maintenance.

Step 2:- Determination of normalised decision matrix

$$f_{ij} = \frac{x_{ij}}{\sqrt{\sum_{i=1}^{m} x_{ij}^2}}, i = 1, \dots, m; j = 1, \dots, n$$

Step 3:- Weighted standard decision matrix selection. The weighted standard decision matrix may be calculated and expressed by multiplying the normalised decision matrix by the weight of decision criteria:

 $v_{ij} = w_j f_{ij}, i = 1, \dots, m; j = 1, \dots, n$

where w_j is the weight of the jth criterion. There are several technique available in the literature for the evaluation of criteria weights. The approach chosen in this paper is the AHP method because of its ability to utilised both qualitative and quantitative information in determining weights of decision criteria.

Step 4:- Determination of the positive-ideal and negative-ideal solutions The positive ideal solution and the negative ideal solution are evaluated respectively as follows:

$$Z^{+} = \left\{ v_{1}^{+}, v_{2}^{+}, \dots, v_{j}^{+} \right\} = \left\{ \left(\max_{i} v_{ij} \mid j \in I \right), \left(\min_{i} v_{ij} \mid j \in I' \right) \right\}$$
$$Z^{-} = \left\{ v_{1}^{-}, v_{2}^{-}, \dots, v_{j}^{-} \right\} = \left\{ \left(\min_{i} v_{ij} \mid j \in I \right), \left(\max_{i} v_{ij} \mid j \in I' \right) \right\}$$

where I is associated with the benefit criteria and I' is associated with cost criteria.

Step 5:- Calculation of the separation measure The separation of each alternative from the positive-ideal solution and from the negative-ideal solution, are evaluated, respectively as:

$$S_{i}^{+} = \left\{\sum_{j=1}^{n} \left(v_{ij} - v_{j}^{+}\right)^{2}\right\}^{\frac{1}{2}} \quad i = 1, 2, \cdots, m; \ j = 1, 2, \cdots, n$$
$$S_{i}^{-} = \left\{\sum_{j=1}^{n} \left(v_{ij} - v_{j}^{-}\right)^{2}\right\}^{\frac{1}{2}} \quad i = 1, 2, \cdots, m; \ j = 1, 2, \cdots, n$$

Step 6:- Calculation of the relative closeness to the positive ideal solution. The relative closeness Pi of the alternatives to the positive ideal solution is evaluated as follows:

$$P_i = \frac{S_i^-}{S_i^+ + S_i^-}, \quad i = 1, \cdots, m$$

The alternative with the maximum Pi value is the optimum solution.

4. Results and Discussions

4.1 AHP-TOPSIS Analysis on Mechanical Characterization of Materials

The mechanical features of CFRP and basalt fibre composites are studied and the impact of material sequencing on different circumstances is established. The mechanical characteristics of the CFP are examined. Foe raking of materials is employed as the following method in the following tables: AHP-TOPSIS technology.

Table	Table 4.1 Experimental design								
S.N o	Composite material	Tensile Strengt	Tensile Modul	Flexural Strength	Flexura l Modulu	Impact Strengt	Hardnes s (BHN)		
1	Epoxy + CCCC	432.93	25930	181.12	30040	4.61	31.4		
2	Epoxy + BBBB	238.88	11130	104.8	10280	6.15	26.53		
3	Epoxy + CBCB	384.82	23700	100	56830	6.15	36.2		
4	Epoxy + BCCB	368.61	24380	104.4	57280	4.61	26.53		
5	Epoxy + CBBC	284.9	20840	104.8	39020	3.84	31.4		
6	Epoxy + CCCC +	433.44	25690	187.32	30250	10.38	37.4		
7	Epoxy + BBBB +	267.36	12880	108.8	47460	6.46	26.53		
8	Epoxy + CBCB +	192.43	17700	98	46820	3.84	31.4		
9	Epoxy + BCCB +	347.26	20840	98.8	40450	3.38	31.4		
10	Epoxy + CBBC +	292.96	21470	101.6	63640	7.38	31.4		
11	Epoxy + CCCC +	387.91	21940	102	52850	5.84	36.2		
12	Epoxy + BBBB +	325.62	11110	112.4	94780	5.53	26.53		
13	Epoxy + CBCB +	349.83	19920	130.74	22180	4.61	36.2		

14	Epoxy + BCCB +	415.45	27750	97.2	29430	5.53	31.4
15	Epoxy + CBBC +	247.67	15900	104	84610	3.38	31.4
16	Epoxy + CCCC +	338.37	24080	100	52110	6	36.2
17	Epoxy + BBBB +	246.47	11390	157.6	22550	6.46	31.4
18	Epoxy + CBCB +	388.05	21640	98.8	52680	6.15	31.4
19	Epoxy + BCCB +	377.63	24330	101.6	96850	3.38	31.4
20	Epoxy + CBBC +	313.18	19140	104	93560	9.23	31.4

Table 4.2 Pair-wise comparison matrix						
Alternatives	Tensile	Tensile	Flexura	Flexural	Impact	Hardnes
AITCI HALIVES	Strength	Modulus	1	Modulu	Strengt	S
Tensile Strength	1	1/3	3	0.2	5	5
Tensile Modulus	3	1	7	0.2	5	5
Flexural Strength	1/3	1/7	1	1/9	3	1
Flexural Modulus	5	5	9	1	7	7
Impact Strength	1/5	0.2	1/3	1/7	1	1/3
Hardness	0.2	0.2	1	1/7	3	1

Material	ΣX _{ij}	Material Property	Weights
		Tensile Strength	0.14502
<u>Fensile Strength</u> Fensile Modulus	0.87010 1.36003	Tensile Modulus	0.22667
lexural	0.34046	Flexural Strength	0.05674
		Flexural Modulus	0.47883
xural	2.87299	Impact Strength	0.03395
pact Strength	0.20367	Hardness	0.05879
ardness	0.35274	Sum	1
ım	6		*

Coherence index mum (CI) of CR: 0.121, Coherence of Coherence (CR):0.098, and CR <0.1 for approval. Until the step above, AHP's method is finished with a weight calculation and a weight coherence check. From here the TOPSIS technique begins.

Table	Table 4.4 Determine Normalized matrix							
S.N o	Composit e material	Tensile Strength	Tensile Modulus	Flexural Strength	Flexural Modulus (MPa)	Impact Strength (MPa)	Hardness (BHN)	
1	Epoxy +	0.99882	0.93441	0.96690	0.31017	0.44412	0.83957	
2	Epoxy +	0.55113	0.40108	0.55947	0.10614	0.59249	0.70936	
3	Epoxy +	0.88783	0.85405	0.53385	0.58678	0.59249	0.96791	
4	Epoxy +	0.85043	0.87856	0.55734	0.59143	0.44412	0.70936	
5	Epoxy +	0.65730	0.75099	0.55947	0.40289	0.36994	0.83957	
6	Epoxy +	1.00000	0.92577	1.00000	0.31234	1.00000	1.00000	
7	Epoxy +	0.61683	0.46414	0.58082	0.49004	0.62235	0.70936	

Optimization of Hybrid CFRP Composites with AHP-Topsis Method in Mechanical charecteriztion

8	Epoxy +	F	0.44396	0.63784	0.52317	0.48343	0.36994	0.83957
9	Epoxy +	F	0.80117	0.75099	0.52744	0.41766	0.32563	0.83957
10	Epoxy +	F	0.67590	0.77369	0.54239	0.65710	0.71098	0.83957
11	Epoxy +	F	0.89496	0.79063	0.54452	0.54569	0.56262	0.96791
12	Epoxy +	F	0.75125	0.40036	0.60004	0.97863	0.53276	0.70936
13	Epoxy +	F	0.80710	0.71784	0.69795	0.22901	0.44412	0.96791
14	Epoxy +	F	0.95849	1.00000	0.51890	0.30387	0.53276	0.83957
15	Epoxy +	F	0.57141	0.57297	0.55520	0.87362	0.32563	0.83957
16	Epoxy +	F	0.78066	0.86775	0.53385	0.53805	0.57803	0.96791
17	Epoxy +	F	0.56864	0.41045	0.84134	0.23283	0.62235	0.83957
18	Epoxy +	F	0.89528	0.77982	0.52744	0.54393	0.59249	0.83957
19	Epoxy +	F	0.87124	0.87676	0.54239	1.00000	0.32563	0.83957
20	Epoxy +	F	0.72255	0.68973	0.55520	0.96603	0.88921	0.83957

Table	Table 4.5 Determine S _i ⁺ matrix					
S.No.	Composite material	Si ⁺ Values				
1	Epoxy + CCCC	0.12627				
2	Epoxy + BBBB	0.16960				
3	Epoxy + CBCB	0.07700				
4	Epoxy + BCCB	0.07633				
5	Epoxy + CBBC	0.11193				
6	Epoxy + CCCC + 1% graphite	0.12566				
7	Epoxy + BBBB + 1% graphite	0.10180				
8	Epoxy + CBCB + 1% graphite	0.10100				
9	Epoxy + BCCB + 1% graphite	0.10879				
10	Epoxy + CBBC + 1% graphite	0.06665				
11	Epoxy + CCCC + 2% graphite	0.08497				
12	Epoxy + BBBB + 2% graphite	0.04363				
13	Epoxy + CBCB + 2% graphite	0.14261				
14	Epoxy + BCCB + 2% graphite	0.12766				
15	Epoxy + CBBC + 2% graphite	0.04309				
16	Epoxy + CCCC + 3% graphite	0.08601				
17	Epoxy + BBBB + 3% graphite	0.14692				
18	Epoxy + CBCB + 3% graphite	0.08545				
19	Epoxy + BCCB + 3% graphite	0.01643				
20	Epoxy + CBBC + 3% graphite	0.02653				

Table	Table 4.6 Determine Si ⁻ matrix				
S.No.	Composite material	Si ⁻ Values			
1	Epoxy + CCCC	0.05763			
2	Epoxy + BBBB	0.00575			
3	Epoxy + CBCB	0.09497			
4	Epoxy + BCCB	0.09588			
5	Epoxy + CBBC	0.05988			
6	Epoxy + CCCC + 1% graphite	0.05846			
7	Epoxy + BBBB + 1% graphite	0.07071			

Ch. Siva RamaKrishna ¹ ,	$Dr.N.Ramanaiah^2$
-------------------------------------	--------------------

Epoxy + CBCB + 1% graphite	0.07078
Epoxy + BCCB + 1% graphite	0.06345
Epoxy + CBBC + 1% graphite	0.10433
Epoxy + CCCC + 2% graphite	0.08672
Epoxy + BBBB + 2% graphite	0.15984
Epoxy + CBCB + 2% graphite	0.03502
Epoxy + BCCB + 2% graphite	0.05856
Epoxy + CBBC + 2% graphite	0.14073
Epoxy + CCCC + 3% graphite	0.08630
Epoxy + BBBB + 3% graphite	0.02498
Epoxy + CBCB + 3% graphite	0.08614
Epoxy + BCCB + 3% graphite	0.16733
Epoxy + CBBC + 3% graphite	0.15884
	Epoxy + BCCB + 1% graphite Epoxy + CBBC + 1% graphite Epoxy + CBBC + 1% graphite Epoxy + CCCC + 2% graphite Epoxy + BBBB + 2% graphite Epoxy + CBCB + 2% graphite Epoxy + CBBC + 2% graphite Epoxy + CBBC + 2% graphite Epoxy + CBCC + 3% graphite Epoxy + BBBB + 3% graphite Epoxy + BCCB + 3% graphite

Table 4.7 Finding Relative Closeness Pi			
S.No.	Composite material	P _i Values	Ranking
1	Epoxy + CCCC	0.31338	17
2	Epoxy + BBBB	0.03278	20
3	Epoxy + CBCB	0.55222	7
4	Epoxy + BCCB	0.55678	6
5	Epoxy + CBBC	0.34853	14
6	Epoxy + CCCC + 1% graphite	0.31751	15
7	Epoxy + BBBB + 1% graphite	0.40990	12
8	Epoxy + CBCB + 1% graphite	0.41202	11
9	Epoxy + BCCB + 1% graphite	0.36837	13
10	Epoxy + CBBC + 1% graphite	0.61018	5
11	Epoxy + CCCC + 2% graphite	0.50508	8
12	Epoxy + BBBB + 2% graphite	0.78559	3
13	Epoxy + CBCB + 2% graphite	0.19717	18
14	Epoxy + BCCB + 2% graphite	0.31447	16
15	Epoxy + CBBC + 2% graphite	0.76560	4
16	Epoxy + CCCC + 3% graphite	0.50086	10
17	Epoxy + BBBB + 3% graphite	0.14533	19
18	Epoxy + CBCB + 3% graphite	0.50201	9
19	Epoxy + BCCB + 3% graphite	0.91058	1
20	Epoxy + CBBC + 3% graphite	0.85690	2

From TOPSIS method the best suitable material is Alternative 19 ie; Epoxy + BCCB + 3% graphite.

Conclusions

The characterization and ranking of mechanical hybrid composites was shown using AHP-TOPSIS method by the addition of graphite powder to composites to enhance the

mechanical properties of epoxy composites. The following findings were reached via study of the composite structure of the CFRP hybrid: In line with the stacking sequence, the change in graphite % has been efficiently generated using CFRP and Basalt composites and also ranking of the hybrid composite.Future researchers may further analyze many more aspects of composites, including the effect of other production technology on the performance of composites.

6.References

[1] Guru raja M.N, A.N Hari Rao,2012, A Review on Recent Applications and Future Prospectus of Hybrid Composites, International Journal of Soft Computing and Engineering (IJSCE) ISSN: 2231-2307, Volume-1.

[2] Ching-Chie Lin, Ya-jung lee, Chu-Sung Hung, 2008, Optimization and experiment of Composite marine propellers, ELSIVER (Science Direct).

[3] Taylor, T.W. and Nayfeh, A.H. (1994) 'Natural frequencies of thick, layered composite plates', Composites Engineering, Vol. 10, pp. 1011–1021.

[4] Ahmed, K. S. and Vijayarangan, S. Tensile, Flexural and Interlaminar Shear Properties of Woven Jute and Jute Glass Fabric Reinforced Polyester Composites, Journal of Materials Processing Technology, 207(1-3), 2008, 330-335.

[5] Shuji Usui, Jon Wadell and Troy Marusich. Finite Element Modeling of Carbon Fiber Composite Orthogonal Cutting and Drilling. CIRP International Conference on High Performance Cutting.2014:211-216.

[6] N. Duboust, C. Pinna, H. Ghadbeigi, S. Ayvar-Soberanis, V.A Phadnis, A. Collis, K. Kerrigan. 2D and 3D Finite Element models for the edge trimming of CFRP CIRP Conference on Modelling of Machining Operations 2017:233-238.

[7] B. J. Rohith, P. Venkataramaiah, P. MohanaReddy, Material Selection forSolar Flat Plate Collectors Using AHP, International Journal of EngineeringResearch and Applications, 2 (2012), pp.1181-1185.

[8] E. Önder, S. Dag, Combining Analytical Hierarchy Process and TOPSISApproaches for Supplier Selection in a Cable Company, Journal of Business, Economics and Finance, 2 (2013), pp.56-74.

[9] M. R. Mansor, S. M. Sapuan, E. S. Zainudin, A. A. Nuraini, A. Hambali, Application of Integrated AHP-TOPSIS Method in Hybrid Natural Fiber Composites Materials Selection for Automotive Parking Brake Lever

Component, 8 (2014), pp. 431-439.

[10] A. A. Maliki, G. Owens, D. Bruce, Combining AHP and TOPSIS Approachesto Support Site Selection for a Lead Pollution Study, 2nd InternationalConference on Environmental and Agriculture Engineering (ICEAE 2012), Jeju Island, Korea (south), 2012. [11] D. N. Ghosh, Analytic Hierarchy Process & TOPSIS Method to Evaluate Faculty Performance in Engineering Education, Universal Journal of Appliedcomputer Science and Technology, 1 (2011), pp. 63-70.